

SIPERNAT® 22 S

Characteristic physico-chemical data*)

Properties and test methods	Unit	Value
Specific surface area (N ₂) Multipoint following ISO 9277	m ² /g	190
DOA absorption ¹⁾ internal method	ml/100g	240
Particle size, d50 Laser diffraction following ISO 13320-1	µm	13.5
Loss on drying 2 h at 105°C following ISO 787-2	%	≤ 7.0
pH value 5 % in water following ISO 787-9	-	6.5
Sieve residue 45 µm spray following ISO 3262-19	%	≤ 1.5
Electrical conductivity 4 % in water following ISO 787-14	µS/cm	≤ 1300
Tamped density not sieved following ISO 787-11	g/l	90
Loss on ignition ²⁾ 2 h at 1000°C following ISO 3262-1	%	≤ 6.0
SiO ₂ content ³⁾ following ISO 3262-19	%	≥ 97
Na content ³⁾ internal method	%	≤ 1.0
Fe content ³⁾ internal method	ppm	≤ 400
Sulfate content ¹⁾ internal method	%	≤ 1.5
HACCP / FAMI-QS	-	yes
Package size (net)	kg	15 (25 lb)
1) based on original substance 2) based on dry substance (2 h/105°C) 3) based on ignited substance (2 h/1000°C) *) The given data are typical values. Specifications on request.		

Registrations

SIPERNAT® 22 S

CAS-No.	112926-00-8 (ex 7631-86-9)
REACH (Europe)	registered
TSCA (USA) AICS (Australia) DSL (Canada)	registered
PICCS (Philippines) IECS (China)	registered
ENCS (Japan)	registered
KECI (Korea)	registered
NZIoC (New Zealand)	registered

SIPERNAT® represents a specific product range of precipitated silica, aluminium and calcium silicates.

SIPERNAT® 22 S is a silica with a high absorption capacity used as a flow and anti-caking agent in many applications as well as a special-purpose ingredient for mechanical graphic papers. In plant protection, this product is recommended as a carrier in solid formulations such as wettable powders (WP) and water-dispersible granules (WG) if grinding has to be avoided.

Safety and handling

Information concerning the safety of this product is listed in the corresponding Material Safety Data Sheet, which will be sent with the first delivery or upon updating.

Such information is also available from: Evonik Industries AG, Product Safety Department, E-Mail: sds-im@evonik.com. We recommend to read carefully the material safety data sheet prior to the use of our product.

Packaging and storage

Our silica products are inert and extremely stable chemically. However, due to their high specific surface area, they can absorb moisture and volatile organic compounds from the surrounding atmosphere. Therefore, we recommend storing the products in sealed containers in a dry, cool place, and removed from volatile organic substances. Even if a product is stored under these conditions, after a longer period it can still pick up ambient moisture over time, which could lead to its exceeding the specified moisture content. For this reason, our recommended use-by date is 24 months after date of manufacture. Product more than 24 months old should be tested for moisture content before use in order to make certain that it is still suitable for the intended application.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Applied Technology Evonik Industries AG

Inorganic Materials
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59-3536
FAX +49 6181 59-4096
ask-si@evonik.com
www.sipernat.com

Europe/ Middle-East/ Africa/ Latin America Evonik Industries AG

Inorganic Materials
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59-8118
FAX +49 6181 59-78118
ask-si@evonik.com
www.sipernat.com

North America Evonik Corporation

Inorganic Materials
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE +1 888 745-4227
FAX +1 732 981-5275
ask-si@evonik.com
www.sipernat.com

Asia-Pacific Evonik Degussa (SEA) Pte. Ltd.

Inorganic Materials
3 International Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6 809 6851
FAX +65 6 809 6651
ask-si-asia@evonik.com
www.sipernat.com